Published online 2024 January 9.

**Research Article** 

## Evaluating the Biocompatibility of Decellularized Pancreas and Its Histological Features as a Support Structure for Adipose Mesenchymal Stem Cell Culture

Neda Farazi<sup>1</sup>, Arash Abdolmaleki <sup>1</sup>/<sub>2</sub>, Asadollah Asadi <sup>1</sup>/<sub>2</sub>, <sup>\*</sup> and Saber Zahri<sup>1</sup>

<sup>1</sup>Department of Biology, University of Mohaghegh Ardabili, Ardabil, Iran

<sup>2</sup>Department of Biophysics, Faculty of Advanced Technologies, University of Mohaghegh Ardabili, Namin, Iran

, Corresponding author: Department of Biology, University of Mohaghegh Ardabili, Ardabil, Iran. Email: asad.asady@gmail.com

Received 2023 August 05; Revised 2023 December 09; Accepted 2023 December 19.

#### Abstract

**Background:** Tissue engineering is a multidisciplinary and interdisciplinary topic that involves the development of biological implants for tissue regeneration intending to improve or enhance tissue or organ function.

**Objectives:** This study aimed to evaluate the mechanical and histological properties of decellularized rat pancreas scaffolds, as well as to investigate the viability of adipose mesenchymal stem cells (MSCs) on the said scaffold for use in regenerative medicine and tissue engineering.

**Methods:** This is an experimental study that was performed in the research laboratory of Mohaghegh Ardabili University. To prepare the scaffold, male Wistar rats were anesthetized with carbon dioxide. After dissecting the mice, their pancreases were isolated and immediately transferred to a phosphate-buffered saline (PBS) solution to prepare them for decellularization. The decellularized scaffolds were evaluated histologically and mechanically. After decellularization, lipid MSCs were injected into de-cell scaffolds in the third passage.

**Results:** Examination of the results of histological evaluations showed that scaffolding was completely decellularized. These results were confirmed by Mason trichrome and Dapi staining (coloring). Specialized tissue assessments by electron microscopy showed that the collagen and elastin strands were relatively conserved in the extracellular matrix (ECM).

**Conclusions:** In general, the result of this research demonstrates the successful decellularization of pancreatic tissue, effective preservation of the ECM of the desired tissue, and the viability of the MSCs on the scaffold resulting from the decellularization of the tissue.

Keywords: Mesenchymal Stem Cell, Decellularized Scaffold, Pancreas, Tissue Engineering, Regenerative Medicine

## 1. Background

The pancreas is a complex organ that contains both exocrine and endocrine functions and secretes the hormone insulin (1). Chronic organ dysfunction is effectively treated with organ transplantation. Organ transplantation is a procedure for repairing and replacing damaged tissues or organs. However, it is frequently hampered by a scarcity of donor tissues/organs and immunological concerns caused by infectious infections (2). Diabetes mellitus is the world's most common, dangerous, and epidemic metabolic illness (3, 4). Diabetes affects approximately 347 million people worldwide and poses a severe threat to their health. The incidence of diabetes is rapidly increasing due to population expansion, aging, obesity, and sedentary lifestyles (4). This disease is also one of the diseases of the pancreas tissue that is related to the hormone insulin. If needed, one of the solutions for treating this disease is a pancreas transplant, which, like other body organ transplants, has many problems (4).

Transplanting the pancreas is a well-established operation that outperforms islet transplantation in terms of long-term metabolic performance. The reason is that islet cell transplantation may result in portal vein hypertension or embolization. However, indications for pancreas transplantation are limited and significant, and sometimes life-threatening problems such as post-transplant pancreatitis, infections, and thrombosis

Copyright © 2024, Farazi et al. This open-access article is available under the Creative Commons Attribution 4.0 (CC BY 4.0) International License (https://creativecommons.org/licenses/by/4.0/), which allows for unrestricted use, distribution, and reproduction in any medium, provided that the original work is properly cited.

continue to cause approximately 10% graft loss (3, 5). With the development of novel tissue engineering techniques based on stem cells and scaffolds (eg, decellularization and recellularization), the above-mentioned issues could be overcome and open a new window in organ or tissue replacement (3, 6).

Engineering human tissues is currently а multidisciplinary and active topic of study (7). Transplantation medicine is an area of applied medical research that is only getting started (2). Regenerative medicine is a large branch in which certain types of cells, primarily stem cells, are employed to repair damaged tissues or organs. The ultimate objective of regenerative medicine is to repair and establish normal organ functioning (8). Although the criteria that bioengineered cells must meet to be regarded as viable therapy have yet to be developed, any possible therapy must be both safe and functionally superior to current therapies (1). Decellularization is a process used in tissue engineering to separate the extracellular matrix (ECM) from the cells in a tissue. This process can lead to the creation of natural scaffolds that are used in the construction of artificial organs and tissue repair (9). The extracellular matrix is a heterogeneous connective network in native tissues and organs that functions in vivo to provide the structural support, mechanical stability, and biochemical signals necessary for tissue morphogenesis and homeostasis. It comprises fibrous glycoproteins, proteoglycans, and small molecules. Fully recreating the ECM features is a huge challenge (7). Decellularization makes it possible to get cell-free, natural ECMs.

The preservation of the 3D structure, which provides support, tensile strength, and attachment sites for cell surface receptors, and the availability of bioactive components that regulate angiogenesis, cell migration, cell proliferation, and cell orientation in wound healing are the 2 main characteristics that explain why decellularized ECM scaffolds can support tissue regeneration (7). Mesenchymal stem cells (MSCs) may be obtained from various sources and rapidly grown in vitro. Researchers have recently discovered that umbilical cord Wharton's jelly is an ideal source for isolating MSCs since it includes wholly defined MSCs with strong proliferation rates. These cells are hypoimmunogenic and release growth factors (8).

Natural polymers, in contrast to synthetic scaffolds, offer superior biocompatibility since acidic byproducts are not formed during decomposition, resulting in no unwanted inflammatory reaction. An alternate approach to treating pancreatic diseases may be possible through the construction of a bioengineered pancreas using the proper combination of cells, biomaterial scaffolds, and physiologically active chemicals (10). In this regard, in tissue engineering and regenerative medicine, to help with problems caused by pancreas transplantation, MSCs and their growth in decellularized scaffolds of pancreatic tissue are used to regenerate the desired tissue. Therefore, the best alternative to pancreas transplantation for clinical use is the combination of pancreatic decellularization scaffold and stem cells (9, 11).

## 2. Objectives

The purpose of this research was to prepare a scaffold from natural pancreatic tissue by decellularization method, evaluate the suitability of the rat pancreas scaffold for MSC culture, and check the survival of these cells on the scaffolds.

## 3. Methods

#### 3.1. Pancreas Decellularization

This study was approved under the ethical approval code of IR.UMA.REC.1400.023.

To prepare the rat's pancreatic cell scaffold, 25 adult male Wister rats weighing 230 - 270 g were purchased and kept in the animal house of Mohaghegh Ardabili University, Faculty of Basic Sciences. According to Mohaghegh Ardabili University's Ethics Committee's endorsement, the rat was sacrificed in a special chamber with an atmosphere containing carbon dioxide. The pancreatic tissue was surgically and carefully dissected to separate it from the surrounding organs, such as the stomach, colon, spleen, and mesenteric tissue. In this study, a healthy pancreas was extracted from 3 animals to be used as native tissue. After cleaning the sample from extra tissues, it was placed in a phosphate-buffered saline (PBS) solution and transferred to the temperature of 4°C for decellularization.

The preparation steps of the pancreas decellularization scaffold were as follows:

1- Immersion: The pancreatic tissue was immersed in distilled water for a duration of 5 h.

2-Ionic detergent: The tissue samples were then placed in a 0.5% sodium dodecyl sulfate (SDS) solution, an ionic detergent, for a period of 12 h.

3- Distilled water wash: After the tissues became translucent, they were washed with distilled water for 15 min.

4- Triton X-100 solution: The tissue samples were transferred to a 1% Triton X-100 solution for a duration of 24 h.

5- Distilled water wash: The target tissue was then washed and re-washed with distilled water for 15 min.

After performing the steps, the decellularized samples were kept in a PBS buffer solution with pH = 7.2 at 4°C.

All decellularization steps were performed at room temperature.

#### 3.2. Histological Analyses

The effectiveness of the decellularization method was evaluated using the hematoxylin and eosin (H&E) staining technique in terms of the removal of cells and the presence of nuclear remnants in histology. Briefly, the decellularized pancreas was fixed with 10% Then, dehydration was done by grading, formalin. increasing the concentration of ethanol, and then xylene. Paraffin-embedded tissues were cut at 4- $\mu$ m thickness, and the tissue sections were deparaffinized with xylene and graded with decreasing ethanol concentration. Slices were stained with H&E and Masson's trichrome to examine the morphology of the intact and acellular pancreas tissue. In the slides stained with H&E, the extracellular fibers are pink under the light microscope, and in Masson's trichrome staining, the nucleus is usually black, and the collagen layers are blue. Masson's trichrome tissue staining is used to see collagen fibers specifically. DAPI staining was used to confirm the removal of cells and examine the residual DNA in the sample of decellularized scaffolds. The DAPI dye binds to 2 pairs of adenine and thymine strands on 2 DNA strands and in a DNA minor groove. Fluorescent blue is visible under UV light.

## 3.3. Decellularized Pancreas Microstructure Analysis by Scanning Electron Microscopy

To examine the exact changes in the level of the decellularized scaffold structure with the intact pancreas tissue (control) with the help of a scanning electron microscope (SEM), briefly, first, the samples were fixed by 2.5% glutaraldehyde for 2 h. Then, dehydration was done with an increasing percentage of ethanol alcohol. After drying, the samples were covered with gold-palladium coating and prepared for imaging and examination using an SEM.

### 3.4. DNA Quantification

DNA extraction was used to evaluate the remaining DNA in the decellularized and intact pancreas. The amount of DNA in native and decellularized tissues was compared by a DNA quantification kit to measure DNA content according to the manufacturer's instructions. DNA isolation is based on cell lysis, followed by selective DNA precipitation. DNA was extracted using the Synaclone extraction kit, and for evaluation, the concentration spectrometry of a DNA nanodroplet at 260 nm was used. A NanoDrop spectrophotometer was also used to determine the purity of nucleic acids by comparing the absorbance at 260 and 280 nm. Briefly, 100  $\mu$ L of protease buffer was added to 30 mg of healthy and decellularized pancreatic tissue. Then, 5  $\mu$ L of protease was added and incubated at 55°C for 1.5 h (until lysis), and then DNA extraction was performed according to the Synaclone kit protocol. Finally, to calculate the DNA concentration relative to the weight of the tissue, the obtained concentration was divided by the weight of the tissue used (ng/mg).

#### 3.5. Sulphated Glycosaminoglycan Content Characterization

All decellularized samples were examined using tissue-specific staining, and the glycosaminoglycan (GAG) content was calculated to validate the preservation of ECM integrity. Glycosaminoglycans play an essential role in the construction of ECM, where they contribute to tissue strength and, in cooperation with collagen, maintain the structure of ECM. To measure GAGs, first, the samples were analyzed by enzymatic digestion using the Kiasyst kit to release the GAG content, and the prepared solutions were transferred to a 96-well plate. Then, in the presence of reactants, a color was produced, read by a microplate spectrophotometer, and absorbed at a wavelength of 510 to 560 nm. The GAG content was determined using a microplate spectrophotometer based on a standard curve created using the standard GAG kit. Reading of the absorbed wavelength was repeated 3 times for every sample.

# 3.6. Seeding Adipose Mesenchymal Stem Cells to Assess Cytocompatibility and Cell Distribution

The succinate dehydrogenase enzyme reduces and breaks down tetrazolium crystals in the MTT test, resulting in the formation of blue, insoluble crystals. An MTT experiment was carried out to assess cell viability in the decellularized pancreatic. Briefly, 96-well microplates containing adipose MSCs were incubated overnight at 37°C in a humid environment containing 5% CO<sub>2</sub>. Adipose MSCs were injected into the decellularized pancreas scaffold using an insulin syringe. Then, the plate was placed in a  $CO_2$  incubator at 37°C for 24 h. Then, 200  $\mu$ L of 0.5 mg MTT was added to each well. After 4 h in the dark phase, 10  $\mu$ L of DMSO was added to each well, and finally, the amount of light absorption at the wavelength of 630 was read by a microplate reader. Absorbance values are related to the number of living cells. Wells without biological scaffolds were considered as controls.

#### 3.7. Amount of Total Protein by the BCA Method

The BCA protein measurement is a method to measure the amount of protein in tissue. The principle of the method is that proteins can reduce  $Cu^{2+}$  to  $Cu^+$  in an alkaline environment, which is known as the Biureh reaction, and a purple color is produced in the presence of bicinchoninic acid. This BCA method is more accurate compared to the Bradford method and the reason is that all chains of peptide bonds participate in the formation of color. Another advantage over the Bradford method is that reagents, such as NP-40, Triton X-100, or SDS, do not interfere.

## 3.8. Statistical Analysis

SPSS version 16.0 was used to conduct the statistical analysis.

Results are reported as SD; each test was run 3 - 6 times.

## 4. Results

#### 4.1. Macroscopic Observations During Decellularization

At first, the technique of physical decellularization of freezing and thawing cycles was performed, which did not bring any specific results. Next, with the completion of chemical decellularization by anion-based detergent (SDS 0.05% and Triton X-100), the morphology of the pancreas tissue was thoroughly evaluated. The decellularized pancreas showed a significant color change (Figure 1B), and a transparent appearance was observed in the evaluation.

In general, macroscopically, a gradual color change was observed during the decellularization process. The produced scaffolds were completely decellularized, but the microgrid remained intact. At the end of the decellularization process, the structure of the organ was still preserved, but the cellular components were removed. The decellularization process continued until the entire pancreas was completely clear. Finally, as shown in Figure 1, the anionic (0.05%) SDS-based detergent concentration caused tissue degradation and disrupted tissue integrity, producing a transparent appearance. After removing the main cellular components of the native pancreas (Figure 1A), the decellularized matrix of the pancreas (Figure 1B) has a different and more straightforward appearance than the control pancreas, indicating proper decellularization.

## 4.2. Extracellular Matrix Scaffold Composition

### 4.2.1. Histological Evaluation of Decellularized Matrices

All decellularized samples were examined using tissue-specific staining (Figure 2).

The results of H&E staining revealed that decellularization was complete, and the decellularized pancreas was entirely free of cells and nuclear materials. Therefore, after the completion of decellularization, cell nuclei were not present in the decellularized pancreas, and no cellular material was stained in the decellularized matrix (Figure 2B).

Additionally, Mason trichrome staining was performed to visualize collagen fibers as abundant components of ECM. They showed that structural components of the pancreas (collagen and elastin fibers) were conserved in the prepared decellularized pancreas (Figure 3).

In the results of Masson trichrome staining, preservation of the ECM, primarily collagen, can be seen in both decellularized (Figure 3B) and intact (control; Figure 3A) pancreas. Collagen was maintained following decellularization, indicating that our decellularization technique effectively eliminated all cellular components while still preserving the makeup of the ECM. Additionally, the decellularized pancreatic scaffold's ECM structure resembled that of a natural pancreas. Microscopically, no relevant differences were observed between the experimental groups (Figure 3), and the decellularized ECM appeared identical to the controls. The DAPI staining of specimens after the decellularization process showed the complete removal of cells. No residual DNA and cell nuclei could be observed in the decellularized group compared to the intact pancreas (Figure 4).

In comparison to the native pancreas (Figure 4A), DAPI staining showed that no cellular material was present in the decellularized scaffold (Figure 4B). This result implies that our decellularization technique retains the composition of the ECM while entirely removing all of the cellular components. In general, DAPI staining showed that decellularization could remove all cellular elements.

#### 4.3. Glycosaminoglycans and Collagens

The amounts of GAG were calculated to confirm the preservation of ECM integrity. A biochemical study was conducted to demonstrate the preservation of the residual GAG content in the matrix. We aimed to quantitatively analyze and validate the retention of the primary ECM components. The GAG content was quantified using the Kiazist GAG assay kit by the manufacturer's instructions, and the results demonstrate no significant difference between the amount of GAG in the scaffold of the pancreas and the control pancreas, indicating that GAG is preserved in the ECM (Figure 5). In fact, bioscaffolds maintained more fabulous GAG material.



Figure 1. The macroscopic view of the decellularization of rat pancreas: A, Native pancreas; and B, decellularized pancreas. The image depicts the change of color from decellularization of the rat pancreas with 0.5% SDS and Triton X-100. The resulting decellularized pancreas appeared translucent.



Figure 2. The hematoxylin and eosin (H&E) staining image of the A, control pancreas and ; B, decellularized pancreas at 10x magnification. The results of H&E staining and checking the general morphology of fresh rat pancreas and acellular pancreas showed that decellularization was complete, and cell removal was visible in the decellularized pancreatic tissue sample.



Figure 3. The image of Mason trichrome staining and comparison of extracellular matrix preservation of the A, intact pancreas and; B, decellularized pancreas of rats at 40x magnification. The results of Mason trichrome staining showed that the structural components of the pancreas (collagen and elastin fibers) were conserved.



Figure 4. The image of the DAPI staining of the pancreas of rats. The DAPI-stained cross sections of the rat pancreas were used to compare the cell nuclei of the A, freshly dissected pancreas and ; B, decellularized pancreas segment. The results showed that the cell nucleuses disappeared in the decellularized pancreas.



**Figure 5.** The sulphated glycosaminoglycan (sGAG) content of native and decellularized pancreases (scaffold). There was a remarkable sGAG content in the decellularized pancreas using the decellularization protocol.

#### 4.4. DNA Quantification

DNA quantification was carried out to further evaluate the effectiveness of decellularization. In a decellularized pancreas, the total DNA content declined significantly compared with the controls. Quantifying of DNA content was done before and after decellularization treatment using the SinaClon kit to verify the efficacy of the process and confirmed effective decellularization in the bioscaffold. Compared to a normal pancreas, double-stranded DNA decreased in the decellularized pancreas, indicating successful cell elimination. The results of comparing the amount of DNA in healthy pancreatic samples with the decellularized pancreatic detected that the amount of DNA significantly was reduced from 57 ng/mg in the native pancreas to 13 ng/mg in the decellularized pancreatic, indicating the removal of cells from the pancreatic tissue. These findings strongly suggest that the decellularization process of the pancreas was successful in effectively eliminating its cellular components (Figure 6).

#### 4.5. Total Protein Content

The results related to the examination of the amount of protein showed the similarity of the amount of total protein in the decellularized scaffold with the intact pancreatic tissue, and no significant decrease was observed in the amount of protein in the decellularized pancreas compared to the control pancreas. In general, in this experiment, as much as the amount of total protein in the ECM of the decellularized tissue was closer to the ECM of the control tissue, the decellularization was done better (Figure 7).



Figure 6. The amount of DNA in decellularized and controlled rat pancreas samples. DNA quantification demonstrated less than 13 ng/mg dry weight of DNA material in the decellularized pancreas.



**Figure 7.** The amount of total protein in the decellularized sample and the control pancreas of the rat

#### 4.6. Scanning Electron Microscopy

To confirm the decellularization process, the prepared scaffold was examined with an electron microscope (Figure 8).

The results related to the ultrastructural evaluation of the decellularized sample showed the complete removal of cells from the scaffold and the preservation of the ECM structure. The decellularized pancreas scaffolds' tissue integrity and microarchitecture were retained; as seen in Figure 8B, a biological porous scaffold with a homogenous structure was made from the voids left behind by cell detachment. This scaffold is suitable for cell seeding.

# 4.7. Cell Adhesion to the Decellularized Scaffold Surface by a Scanning Electron Microscopy and Cell Viability

Adipose MSCs' adherence and maintenance to the decellularized scaffold of rat pancreas by electron microscope were evaluated and studied in vitro. By



Figure 8. The scanning electron microscopy (SEM) of A, native and; B, decellularized pancreas. The SEM confirmed a lot of cellular material in the native pancreas. In both bioscaffolds, tissue integrity was preserved.

examining the results of the prepared image, the adhesion of the cells on the scaffold can be recognized (Figure 9).

The MTT assay showed that adipose MSCs cultured in the decellularized pancreas displayed viability comparable to the positive control, indicating that the bioscaffold was not cytotoxic and that cells may proliferate there. This means that the scaffold of a decellularized pancreas showed signs of cell survival and proliferation after 8 days of culture, but the evaluation of the results of cell viability on different scaffolds showed a significant decrease in cell viability on decellularized scaffolds compared to the control group (P < 0.01). Therefore, the growth and proliferation of fat MSCs also depend on environmental factors (Figure 10).

The viability and proliferation of MSCs were investigated after culture. The results showed that MSCs survived in the decellularized scaffold from pancreatic tissue. The experiments were performed in triplicate.

#### 5. Discussion

To completely destroy all cellular components, some decellularization methods are used, such as melting and freezing cycles, which are known as physical methods and mechanical stimulation. However, this method does not guarantee the preservation of the ECM microstructure, which is essential for tissue engineering (9, 12). Extracellular matrix proteins support angiogenesis in addition to cell transport, proliferation, and differentiation (9). Extracellular matrix components, as well as 3D- and microstructure and physical characteristics, were retained in our approach for complete organ decellularization. Data from Masson trichrome staining showed that the collagen composition of the decellularized pancreatic scaffold was identical to that of the natural pancreas.

In pancreatic, diabetes mellitus causes a decrease in function and/or absolute numbers of insulin-producing cells. Islet transplantation is being studied as a potential solution, and developments in tissue engineering approaches can help increase pancreatic islet survival and performance. Transplanted pancreatic tissue develops anoikis, hypoxia, and an immunological response driven by inflammation, resulting in early graft damage and failure (12). The need for transplantation and repair of pancreatic tissue is one of the biggest human concerns due to the many problems in organ transplantation, and scientists are always looking for ways with fewer complications for organ transplantation (13). Decellularized organs can now be used as scaffolds for cell treatments because of recent advances in tissue engineering. This is because it can preserve natural ECM,



Figure 9. Scanning electron micrographs showing that cells adhered effectively to the decellularized pancreas, according to scanning electron microscopy images

and the vascular, decellularized pancreas might be a suitable substrate (14).

Tissue engineering and regenerative medicine have increased the use of biological materials by providing new strategies to solve organ transplant problems and suggesting innovative ways to develop new treatments. Providing suitable conditions for better repair, regeneration, and proliferation of cells is done by pancreatic tissue engineering scaffolds (13). More challenging than 2-dimensional culture is whole organ bioengineering because it requires a complicated and cell-supporting framework to distribute nutrients to all organ parts. The 3D structure is critical for subsequent cell survival and performance (13, 14). Clinical trials have been conducted with bioengineered tissues and organs, such as synthetic bladders, tracheas, nasal cartilage, and tubular tissue (15, 16).

For the first time, several organs (such as the heart, lung, and liver) were decellularized after coronary arteries were decellularized (17-19). Successful decellularization includes eliminating all cells and maintaining ECM components and a vasculature that resembles that of the original tissue. Rat, pig, and human pancreases have

all been subjected to various decellularization methods (18, 19). Therefore, one of the biggest concerns among tissue engineering and regenerative medicine scientists is to perform the decellularization technique with minor damage to the ECM while preserving it and removing the maximum number of cells. The decellularization technique, which has recently been used in tissue engineering by removing all cellular material from an organ, can provide us with a 3D biocompatible scaffold; thus, stem cells can be grown in it (20).

Physical techniques (such as thawing and freezing cycles) and chemical techniques (such as the use of detergents) are used in tissue decellularization (21). Examining and evaluating the results of decellularization showed that the cellular components of the control pancreas were removed acceptably; the general framework of the tissue and biomechanical properties, which are essential in scaffolds, were preserved, which is a sign of successful decellularization. Goh et al., who had performed the same method of pancreatic decellularization, achieved similar results in H&E staining of the scaffolds obtained from this research (22, 23).

The scanning electron microscopy showed that a



Figure 10. The MTT chart. Cell viability comparison between cultured mesenchymal stem cells (MSCs) on the decellularized scaffold (cell + scaffold) and MSCs without scaffold (control) after 24 h (\*\* P < 0.01)

3-dimensional network of collagen fibers remained from decellularization, collagen being the most abundant pancreatic ECM protein. Data from Masson trichrome staining showed that the collagen composition of the decellularized pancreatic scaffold was identical to that of the natural pancreas (24). While alkaline and acid therapies can eliminate biological components and nucleic acids like RNA and DNA, they can degrade ECM components like GAGs (25). Nonionic detergents (such as Triton X-100) affect lipid-lipid and lipid-protein interactions, although they are intended to retain protein cell particles while destroying the basement membrane (26). The ionic detergent SDS can remove nuclear remnants and cytoplasmic proteins altogether. While effectively dissolves cell membranes, the native tissue structure with minimal damage to the ECM is mostly preserved by this detergent (27).

Studies have shown that damage to any of the components of the ECM, such as collagen, reduces the mechanical strength of tissue engineering scaffolds. In this case, the shelf life of stem cells in such scaffolds is surprisingly reduced. The use of trypsin for decellularization has been shown to cause harm to ECM components (28).

In Guo et al.'s study, decellularization of the whole

pancreas was performed using perfusion with Triton X-100 and  $NH_4OH$  solution. In our study, Triton X-100 was used to effectively remove nuclear and cytoplasmic fragments from SDS, as well as to affect lipid-lipid and lipid-protein interactions (29).

In recent studies, it was shown that a mouse pancreatic bioscaffold based on SDS/Triton perfused through the anterior hepatic portal vein might regenerate the natural pancreas for pancreatic tissue engineering (30). The goal of this study was to use a technique to generate a decellularized pancreatic matrix for pancreas tissue engineering using a mix of Triton and SDS.

In the study by Sevastianov et al., Triton X-100 and SDS were used to decellularize pancreatic tissue, and the results showed that the pancreatic tissue was well decellularized and the basic proteins of the ECM were well preserved (31). Therefore, the technique allowed total cell removal while maintaining the ECM structure (sGAG and collagen content) and vasculature.

The results showed that the ECM of the decellularized pancreatic scaffold provided a suitable microenvironment for cell adhesion. The adipose MSCs survived in these scaffolds and have high durability. Based on our findings, it was observed that the pancreas became translucent, and a higher percentage of the remaining DNA was eliminated.

#### 5.1. Conclusions

This research showed that the decellularized pancreas scaffolds, whose decellularization was done correctly and efficiently according to the results obtained, considering the integrity of the cells in the scaffold, can be a suitable platform for the growth of MSCs.

This study can significantly contribute to the development of engineered pancreas tissue transplantation and provide an innovative approach for tissue engineering experiments and regenerative medicine. Therefore, it can be further investigated as an ideal scaffold in future research, especially in in vivo conditions.

## Acknowledgments

The authors would like to thank the Research Council of the University of Mohaghegh Ardabili for the financial support of this study.

## Footnotes

**Authors' Contribution:** Study concept and design: N.F. and A.A.A. Acquisition of data: N.F. Analysis and interpretation of data: A.A. and A.A.A. Drafting of the manuscript: N.F. Critical revision of the manuscript for important intellectual content: S.Z. and A.A.A. Statistical analysis: A.A. Study supervision: S.Z. and A.A.A. Conceive and design the evaluation and draft the manuscript: A.A.A. and N.F. Participate in designing the evaluation, perform parts of the statistical analysis, and help to draft the manuscript: A.A. Re-evaluate the clinical data, revise the manuscript, perform the statistical analysis, and revise the manuscript: S.Z. Collect the clinical data, interpret them, and revise the manuscript: A.A. and N.F. Re-analyze the clinical and statistical data and revise the manuscript: A.A.A. and S.Z. All authors read and approved the final manuscript.

**Conflict of Interests:** The authors have no conflict of interest, and they thank the University of Mohaghegh Ardabili for funding this research.

**Data Availability:** The dataset presented in the study is available on request from the corresponding author during submission or after publication.

**Ethical Approval:** This study was approved under the ethical approval code of IR.UMA.REC.1400.023.

**Funding/Support:** This study was supported by the University of Mohaghegh Ardabili (grant number: 9822364105).

#### References

- Ellis C, Ramzy A, Kieffer TJ. Regenerative medicine and cell-based approaches to restore pancreatic function. *Nat Rev Gastroenterol Hepatol.* 2017;14(10):612–28. [PubMed ID: 28811674]. https://doi.org/10. 1038/nrgastro.2017.93.
- Rana D, Zreiqat H, Benkirane-Jessel N, Ramakrishna S, Ramalingam M. Development of decellularized scaffolds for stem cell-driven tissue engineering. *J Tissue Eng Regen Med.* 2017;**11**(4):942–65. [PubMed ID: 26119160]. https://doi.org/10.1002/term.2061.
- Napierala H, Hillebrandt KH, Haep N, Tang P, Tintemann M, Gassner J, et al. Engineering an endocrine Neo-Pancreas by repopulation of a decellularized rat pancreas with islets of Langerhans. *Sci Rep.* 2017;7:41777. [PubMed ID: 28150744]. [PubMed Central ID: PMC5288794]. https://doi.org/10.1038/srep41777.
- 4. Niknamasl A, Ostad SN, Soleimani M, Azami M, Salmani MK, Lotfibakhshaiesh N, et al. A new approach for pancreatic tissue engineering: Human endometrial stem cells encapsulated in fibrin gel can differentiate to pancreatic islet beta-cell. *Cell Biol Int.* 2014;**38**(10):1174-82. [PubMed ID: 24905796]. https: |/doi.org/10.1002/cbin.10314.
- Shupe T, Williams M, Brown A, Willenberg B, Petersen BE. Method for the decellularization of intact rat liver. Organogenesis. 2010;6(2):134–6. [PubMed ID: 20885860]. [PubMed Central ID: PMC2901817]. https:// doi.org/10.4161/org.6.2.11546.
- Hashemi J, Pasalar P, Soleimani M, Arefian E, Khorramirouz R, Akbarzadeh A, et al. Decellularized pancreas matrix scaffolds for tissue engineering using ductal or arterial catheterization. *Cells Tissues Organs*. 2018;**205**(2):72–84. [PubMed ID: 29742511]. https://doi. org/10.1159/000487230.
- Dussoyer M, Michopoulou A, Rousselle P. Decellularized scaffolds for skin repair and regeneration. *Applied Sciences*. 2020;10(10). https:// doi.org/10.3390/app10103435.

- Wu D, Wan J, Huang Y, Guo Y, Xu T, Zhu M, et al. 3D culture of MIN-6 cells on decellularized pancreatic scaffold: In vitro and in vivo study. *Biomed Res Int.* 2015;2015:432645. [PubMed ID: 26688810]. [PubMed Central ID: PMC4672115]. https://doi.org/10.1155/2015/432645.
- Kazemi T, Mohammadpour AA, Matin MM, Mahdavi-Shahri N, Dehghani H, Kazemi Riabi SH. Decellularized bovine aorta as a promising 3D elastin scaffold for vascular tissue engineering applications. *Regen Med.* 2021;16(12):1037–50. [PubMed ID: 34852636]. https://doi.org/10.2217/rme-2021-0062.
- Perez-Basterrechea M, Esteban MM, Vega JA, Obaya AJ. Tissue-engineering approaches in pancreatic islet transplantation. *Biotechnol Bioeng.* 2018;115(12):3009–29. [PubMed ID: 30144310]. https://doi.org/10.1002/bit.26821.
- Nasrollahi Nia F, Asadi A, Zahri S, Abdolmaleki A. Biosynthesis, characterization and evaluation of the supportive properties and biocompatibility of DBM nanoparticles on a tissue-engineered nerve conduit from decellularized sciatic nerve. *Regen Ther.* 2020;**14**:315–21. [PubMed ID: 32467828]. [PubMed Central ID: PMC7243182]. https://doi. org/10.1016/j.reth.2020.03.004.
- Guruswamy Damodaran R, Vermette P. Decellularized pancreas as a native extracellular matrix scaffold for pancreatic islet seeding and culture. J Tissue Eng Regen Med. 2018;12(5):1230-7. [PubMed ID: 29499099]. https://doi.org/10.1002/term.2655.
- Berkova Z, Zacharovova K, Patikova A, Leontovyc I, Hladikova Z, Cerveny D, et al. Decellularized Pancreatic Tail as Matrix for Pancreatic Islet Transplantation into the Greater Omentum in Rats. *J Funct Biomater*. 2022;**13**(4). [PubMed ID: 36278640]. [PubMed Central ID: PMC9589982]. https://doi.org/10.3390/jfb13040171.
- Welman T, Michel S, Segaren N, Shanmugarajah K. Bioengineering for organ transplantation: Progress and challenges. *Bioengineered*. 2015;6(5):257-61. [PubMed ID: 26259720]. [PubMed Central ID: PMC4825836]. https://doi.org/10.1080/21655979.2015.1081320.
- Raya-Rivera A, Esquiliano DR, Yoo JJ, Lopez-Bayghen E, Soker S, Atala A. Tissue-engineered autologous urethras for patients who need reconstruction: An observational study. *Lancet*. 2011;**377**(9772):1175–82. [PubMed ID: 21388673]. [PubMed Central ID: PMC4005887]. https:// doi.org/10.1016/S0140-6736(10)62354-9.
- Raya-Rivera AM, Esquiliano D, Fierro-Pastrana R, Lopez-Bayghen E, Valencia P, Ordorica-Flores R, et al. Tissue-engineered autologous vaginal organs in patients: A pilot cohort study. *Lancet.* 2014;**384**(9940):329–36. [PubMed ID: 24726478]. https://doi.org/10.1016/S0140-6736(14)60542-0.
- Fulco I, Miot S, Haug MD, Barbero A, Wixmerten A, Feliciano S, et al. Engineered autologous cartilage tissue for nasal reconstruction after tumour resection: An observational first-in-human trial. *Lancet.* 2014;**384**(9940):337–46. [PubMed ID: 24726477]. https://doi.org/10.1016/S0140-6736(14)60544-4.
- Price AP, Godin LM, Domek A, Cotter T, D'Cunha J, Taylor DA, et al. Automated decellularization of intact, human-sized lungs for tissue engineering. *Tissue Eng Part C Methods*. 2015;21(1):94–103. [PubMed ID: 24826875]. [PubMed Central ID: PMC4290793]. https:// doi.org/10.1089/ten.TEC.2013.0756.
- Ott HC, Matthiesen TS, Goh SK, Black LD, Kren SM, Netoff TI, et al. Perfusion-decellularized matrix: Using nature's platform to engineer a bioartificial heart. *Nat Med.* 2008;14(2):213-21. [PubMed ID: 18193059]. https://doi.org/10.1038/nm1684.
- McInnes AD, Moser MAJ, Chen X. Preparation and use of decellularized extracellular matrix for tissue engineering. *J Funct Biomater*. 2022;**13**(4). [PubMed ID: 36412881]. [PubMed Central ID: PMC9680265]. https://doi.org/10.3390/jfb13040240.
- Gilbert-Honick J, Grayson W. Vascularized and innervated skeletal muscle tissue engineering. *Adv Healthc Mater*. 2020;9(1). e1900626. [PubMed ID: 31622051]. [PubMed Central ID: PMC6986325]. https://doi. org/10.1002/adhm.201900626.

- Goh SK, Bertera S, Olsen P, Candiello JE, Halfter W, Uechi G, et al. Perfusion-decellularized pancreas as a natural 3D scaffold for pancreatic tissue and whole organ engineering. *Biomaterials*. 2013;34(28):6760-72. [PubMed ID: 23787110]. [PubMed Central ID: PMC3748589]. https://doi.org/10.1016/ji.biomaterials.2013.05.066.
- Goh SK, Bertera S, Richardson T, Banerjee I. Repopulation of decellularized organ scaffolds with human pluripotent stem cell-derived pancreatic progenitor cells. *Biomed Mater.* 2023;18(2). [PubMed ID: 36720168]. https://doi.org/10.1088/1748-605X/acb7bf.
- Liu X, Zhao N, Liang H, Tan B, Huang F, Hu H, et al. Bone tissue engineering scaffolds with HUVECs/hBMSCs cocultured on 3D-printed composite bioactive ceramic scaffolds promoted osteogenesis/angiogenesis. J Orthop Translat. 2022;37:152–62. [PubMed ID: 36380884]. [PubMed Central ID: PMC9640992]. https://doi.org/10.1016/j.jot.2022.10.008.
- Klak M, Lojszczyk I, Berman A, Tymicki G, Adamiok-Ostrowska A, Sierakowski M, et al. Impact of porcine pancreas decellularization conditions on the quality of obtained dECM. *Int J Mol Sci.* 2021;**22**(13). [PubMed ID: 34209772]. [PubMed Central ID: PMC8267664]. https:// doi.org/10.3390/ijms22137005.
- Hashemi J, Barati G, Bibak B. Decellularized matrix bioscaffolds: Implementation of native microenvironment in pancreatic tissue engineering. *Pancreas*. 2021;50(7):942–51. [PubMed ID: 34643609]. https://doi.org/10.1097/MPA.00000000001868.

- Moffat D, Ye K, Jin S. Decellularization for the retention of tissue niches. J Tissue Eng. 2022;13:20417314221101200. [PubMed ID: 35620656]. [PubMed Central ID: PMC9128068]. https://doi.org/10.1177/20417314221101151.
- Zhang X, Chen X, Hong H, Hu R, Liu J, Liu C. Decellularized extracellular matrix scaffolds: Recent trends and emerging strategies in tissue engineering. *Bioact Mater*. 2022;10:15–31. [PubMed ID: 34901526]. [PubMed Central ID: PMC8637010]. https://doi.org/10.1016/j.bioactmat.2021.09.014.
- Guo Y, Wu C, Xu L, Xu Y, Xiaohong L, Hui Z, et al. Vascularization of pancreatic decellularized scaffold with endothelial progenitor cells. *JArtifOrgans*. 2018;21(2):230–7. [PubMed ID: 29368270]. https://doi.org/ 10.1007/s10047-018-1017-6.
- Remaggi G, Barbaro F, Di Conza G, Trevisi G, Bergonzi C, Toni R, et al. Decellularization detergents as methodological variables in mass spectrometry of stromal matrices. *Tissue Eng Part C Methods*. 2022;28(4):148–57. [PubMed ID: 35357965]. https://doi.org/10.1089/ten. TEC.2021.0191.
- Sevastianov VI, Ponomareva AS, Baranova NV, Kirsanova LA, Basok YB, Nemets EA, et al. Decellularization of human pancreatic fragments with pronounced signs of structural changes. *Int J Mol Sci.* 2022;24(1). [PubMed ID: 36613557]. [PubMed Central ID: PMC9820198]. https://doi. org/10.3390/ijms24010119.