

# Formulation and Evaluation of Sustained Release Dosage Form of Nifedipine Hydrochloride Using Hydrophilic Polymers

Mohammad Barzegar-Jalali<sup>a,b</sup>, Jalal Hanaee<sup>b,c</sup>, Yadollah Omid<sup>d,e</sup>, Saeed Ghanbarzadeh<sup>b,f</sup>, Fatemeh Mizani Oskoi<sup>b,f</sup>, Nazila Jafari Aghdam<sup>b,f</sup>, Khosro Adibkia<sup>a,b\*</sup>

<sup>a</sup>Biotechnology Research Center, Tabriz University of Medical Science, Tabriz, Iran.

<sup>b</sup>Faculty of Pharmacy, Tabriz University of Medical Science, Tabriz, Iran.

<sup>c</sup>School of Life Sciences, University of Bradford, Bradford, UK.

<sup>d</sup>Research Center for Pharmaceutical Nanotechnology, Tabriz University of Medical Sciences, Tabriz, Iran.

<sup>e</sup>Ovarian Cancer Research Center, Perelman School of Medicine, University of Pennsylvania, Philadelphia, USA.

<sup>f</sup>Students Research Committee, Tabriz University of Medical Sciences, Tabriz, Iran

## ARTICLE INFO

### Article Type:

Research Article

### Article History:

Received: 2013-01-25

Revised: 2013-02-03

Accepted: 2013-02-15

ePublished: 2013-02-18

### Keywords:

Matrix Tablet

Nifedipine

Sustained Release

Direct Compression

## ABSTRACT

Sustained release oral delivery systems are designed to achieve therapeutically effective concentrations of drug in the systemic circulation over an extended period of time. The purpose of the present investigation was to design and evaluate sustained release matrix tablets of nifedipine, a poorly water soluble drug, employing hydroxypropyl methyl cellulose (HPMC) and ethyl cellulose (EC) as hydrophilic polymers. Direct compression method was used to prepare matrix tablets. Drug content uniformity, friability test were performed and the *in vitro* drug release profiles were compared with the innovator product (Procardia) benefiting similarity factor ( $f_2$ ) and difference factor ( $f_1$ ). In all formulations content uniformity was in the acceptable range. Most of the prepared formulations passed friability test. Formulation containing HPMC and EC in the ratio of 88.5:5 showed acceptable dissolution properties compared to reference formulation. Fitting the release data to the kinetic models indicated that the best fitted kinetic model for the prepared matrix tablets and Procardia were zero order and Weibull model, respectively. This study indicates that the hydrophilic matrix tablets of nifedipine prepared using HPMC and EC can successfully be employed as sustained release matrix tablet in order to improve patient compliance.

\*Corresponding author: Khosro Adibkia, E-mail: adibkia@tbzmed.ac.ir

## Introduction

Nifedipine (NF) is a yellow crystalline substance, practically insoluble in water but soluble in ethanol. NF is a selective calcium-channel blocker and a peripheral arterial vasodilator which acts directly on vascular smooth muscle. NF is widely used in the treatment of angina pectoris and systemic hypertension. It is a poorly soluble drug and its absorption from gastrointestinal tract is limited by dissolution rate. It has a short biological half-life (4 hrs). Absorption of NF is poor following administration orally via immediate release dosage forms. It exhibits 45-65% oral bioavailability due to hepatic first pass metabolism. Immediate release formulations of NF clearly show fluctuation in drug plasma concentration results in specific side effects like increase in heart rate. Sublingual NF has been used in hypertensive emergencies, however, was found to be unsafe [1-6].

Sustained release formulations are drug delivery systems that are designed to achieve an expanded therapeutic effect by continuously releasing of drug over an extended period of time after administration of a single dose. To reduce the frequency of administration and to improve patient's compliance, a once daily sustained-release formulation of NF is desirable. Most commonly used method to control the drug release is incorporation of drug in a matrix system. The direct compressed matrix tablet has been used for decades due to its simplicity and cost efficiency comparison with other drug delivery systems [2, 3, 7-10]. Hydrophilic polymers are widely used in matrix systems. HPMC is the hydrophilic polymer used for the preparation of oral controlled drug delivery systems as a release retarding carrier. Types, concentration and weight ratio of polymers will lead to high variation of drug release [6, 11-14]. The main objective of this work was to develop and characterize a directly compressed sustained release matrix tablet of NF using HPMC and EC.

## Materials and methods

### Materials

Nifedipine powder (Sanofichimie, Spain), Hydroxypropyl methyl cellulose,  $\eta=16.96$  cps (Yocohama, Japan), Ethyl cellulose (Hercules,

Island), Magnesium stearate (Merck, Germany), Methanol (Merck, Germany), Nifedipine film coated tablet 10 mg (Batch: 168, Chimidar, Iran), Nifedipine soft gel capsules 10 mg (Batch: AM650, Apotex INC, Canada), Procardia tablet 30 mg (Batch: F7754, Pratt, USA).

### Tablet preparation and evaluation

Drug and polymers were weighed separately for each formulation as illustrated in Table 1. Tablets weight was 500 mg for all formulations. NF and polymers (HPMC and EC) were hand blended for 2 hrs. Magnesium Stearate (MgSt) (0.5%) was added and blended for another 10 min. The mixture was compressed directly using a laboratory single punch machine (Riken, Japan) equipped with 10 mm round punch and die set for three sec at different pressures (Table 1).

**Table 1.** The composition of the formulations, pressure used for compression and rpm applied in dissolution test

| Formulation code | NF (%w/w) | MgSt (%w/w) | HPMC (%w/w) | EC (%w/w) | Pressure (kg/cm <sup>2</sup> ) |
|------------------|-----------|-------------|-------------|-----------|--------------------------------|
| F1               | 6         | 0.5         | 93.5        | 0         | 140                            |
| F2               | 6         | 0.5         | 93.5        | 0         | 280                            |
| F3               | 6         | 0.5         | 93.5        | 0         | 415                            |
| F4               | 6         | 0.5         | 93.5        | 0         | 550                            |
| F5               | 6         | 0.5         | 88.5        | 5         | 550                            |
| F6               | 6         | 0.5         | 83.5        | 10        | 550                            |
| F7               | 6         | 0.5         | 13.5        | 80        | 550                            |
| F8               | 6         | 0.5         | 0           | 93.5      | 550                            |


The prepared matrix tablets were characterized immediately for friability and drug content. Friability (n=10) was determined in a friabilator machine (Erweka, Germany) for 4 minutes at a speed of 25 rpm. Drug content was analyzed by measuring the absorbance of standard and samples at  $\lambda = 233$  nm using UV/Visible spectrophotometer (Shimadzu, Japan).



### In vitro drug release study

Calibration curve was linear in the range of 0.775-15.5 mg/L in solution of methanol: water (20:80) at two wave length, 238 and 334 nm ( $r^2=0.9999$ ). Since the excipients of the softgel bared a UV absorption in wave length 238 nm; so therefore, 334 nm was directed for evaluation of drug release from the softgel.

*In vitro* dissolution studies were conducted using 1000 ml distilled water under stirring rate of 150 rpm for 10 hrs. The temperature was maintained at  $37 \pm 0.5$  °C. At the time intervals of 0.5 hrs, 5 ml of samples were taken out and replaced with water immediately. The withdrawn volume of dissolution medium was filtered using 0.45  $\mu$ m filter and the filtrate was analyzed by UV spectrophotometer<sup>[15]</sup>. The amount of drug in the samples was calculated from calibration curve obtained from the standard solution of the drug. The percentage of cumulative drug released was plotted against time. Release profiles of the tablets are summarized in Fig. 1.



**Fig. 1.** Drug release profiles for prepared formulations, NF tablet available in the market, softgel and reference product (Procardia).

To evaluate and compare dissolution profiles, the release data was analyzed using dissolution similarity factor ( $f_2$ ) and difference factor ( $f_1$ ). If  $f_1 < 15$  and  $50 < f_2 < 100$ , two dissolution profiles are verified similar. The equations for calculating  $f_2$  and  $f_1$  are given below.

$$f_2 = 50 \log \left\{ \left[ 1 + \frac{1}{n} \sum (R_t - T_t)^2 \right]^{-0.5} \times 100 \right\} \quad (1)$$

$$f_1 = \left\{ \frac{\sum (R_t - T_t)}{\sum R_t} \right\} \times 100 \% \quad (2)$$

Where  $R_t$  and  $T_t$  are the cumulative percentage of dissolved drug for a reference and test formulation at time  $t$ , respectively,  $n$  is the number of time points<sup>[14, 16-18]</sup>.

To find out the mechanism of drug release, the release kinetics data from all matrixes were fitted to various equations including zero order, first order, Higuchi, Peppas, Weibull, linear Wagner, and log Wagner<sup>[7, 9, 19, 20]</sup>. The accuracy and prediction ability of the models were compared by calculation of squared correlation coefficients ( $r^2$ ) and percent error (PE).

## Results and discussion

### Tablet evaluation

Friability of the tablets excluding formulations F1 and F2 were within the acceptable range of  $< 1\%$  specifying that tablet surfaces were strong enough to withstand mechanical force or erosion during storage and transport and until consumption.<sup>[15]</sup> Formulations F1 and F2 which were compressed under pressures 280 and 415 kg/cm<sup>2</sup> were excluded from further tests. The tablets showed a high degree of drug content uniformity, so that drug content was more than 95% for all the tablets.

### In vitro drug release study

The release profiles of NF from different formulated matrix tablets are illustrated in Fig. 1. NF release rate from the prepared matrix tablets was slow and the drug release prolonged more than 10 hours. Matrix tablets F3, F4, F5 and F6 provided a release profile comparable to the innovator's sustained released tablet.

### Effect of polymer content on drug release

As shown in Fig. 1, existence of EC in concentration 5% (F5) could sustain release of NF more than formulation F4 containing no EC in its composition. Increasing the amount of EC to 10 % (F6) could not prolonged the drug release rate more than F5 ( $f_2=37.46$  and  $f_1=72.51$ ) indicating that 5% EC could be the optimum amount of polymer to extend NF release from matrix tablets prepared from HPMC and EC.

At higher polymer concentrations, the viscosity of the gel matrix is increased which results in a decrease in the effective diffusion of the drug. This indicates that drug/polymer ratio is important factors affecting the rate of drug release from HPMC and EC matrices. In the other word, factors that may contribute to variations in drug dissolution profiles as a function of changes in total polymer concentration include differences in water penetration rate, water absorption capacity and polymer swelling [1, 7, 10, 13, 14, 21-23]

### Effect of compression pressure on NF release

Even though the formulations F1, F2, F3 and F4 prepared with the same composition but different compression pressure was applied. Comparative dissolution profiles of F3 and F4 are illustrated in Fig. 1. As shown, release profiles were similar, so that the calculated  $f_2$  and  $f_1$  for F3 and F4 were 83.66

and 3.58, respectively indicating similarity between two release profiles. Therefore compression pressures of 415 and 550 kg/cm<sup>2</sup> were found to be adequate pressure for preparation of NF matrix tablets.

### Kinetic analysis of dissolution data

In order to describe the kinetics of the drug release process, different models were applied to fit the dissolution data. Squared correlation coefficient ( $r^2$ ) and percent error (PE) resulted from fitting of the release data to the kinetic models are presented in Table 2. Drug release data for formulations F3, F4, F5 and F6 fitted best to the Weibull equation ( $r^2=0.9809-0.9913$  and PE= 5.8-9.3), where the predominant model for Procardia was zero order. A high correlation with zero order kinetic was also found to the prepared formulations ( $r^2 > 0.9$  and PE < 12).

**Table 2.** Squared correlation coefficients (RSQ) and percent error (PE) of the kinetic models used for NF matrix tablets

| Model              |     | F3     | F4     | F5     | F6     | Procardia |
|--------------------|-----|--------|--------|--------|--------|-----------|
| Zero order         | RSQ | 0.9496 | 0.9458 | 0.9499 | 0.9410 | 0.9899    |
|                    | PE  | 11.43  | 12.68  | 12.11  | 10.96  | 6.31      |
| First order        | RSQ | 0.9875 | 0.9868 | 0.9768 | 0.9774 | 0.9744    |
|                    | PE  | 12.81  | 14.20  | 18.15  | 18.15  | 15.33     |
| Higuchi            | RSQ | 0.9687 | 0.9750 | 0.9577 | 0.9561 | 0.8794    |
|                    | PE  | 12.41  | 14.91  | 16.53  | 13.40  | 21.54     |
| Peppas             | RSQ | 0.9807 | 0.9790 | 0.9777 | 0.9678 | 0.9455    |
|                    | PE  | 9.98   | 14.53  | 11.94  | 14.54  | 12.47     |
| Weibull            | RSQ | 0.9913 | 0.9855 | 0.9837 | 0.9836 | 0.9534    |
|                    | PE  | 5.87   | 8.80   | 9.30   | 8.65   | 8.89      |
| Linear probability | RSQ | 0.5730 | 0.5466 | 0.5754 | 0.5990 | 0.5698    |
|                    | PE  | 32.09  | 31.93  | 35.30  | 31.78  | 38.52     |
| Log- probability   | RSQ | 0.9870 | 0.9792 | 0.9773 | 0.9900 | 0.9436    |
|                    | PE  | 15.92  | 14.96  | 16.13  | 11.39  | 12.88     |

### Conclusion

The current study indicates that the hydrophilic matrix tablet of NF prepared using HPMC and EC can successfully be employed as an oral controlled release dosage form. For formulations F4, F5 and F6 *in vitro* dissolution studies indicated a sustained release pattern throughout 10 hrs of the study which

was comparable with innovator product's release

profile. Although, according to  $f_1$  and  $f_2$  values, the prepared formulations could not sustain the drug release similar to Procardia, but they were able to prolong the drug release more than 10 hrs with a parallel release pattern. Results of the present study demonstrated that combination of HPMC and EC would be useful in the preparation of NF sustained

release matrix tablets with desired release profile. The sustained release tablets can be used to reduce the frequency of administration and decrease the dose dependent side effects associated with repeated administration of conventional NF tablets. The formulation method employed is simple and could be adaptable for industrial scale up.

### Conflict of interest

Authors certify that no actual or potential conflict of interest in relation to this article exists.

### Acknowledgement

The authors would like to thank Biotechnology Research Center, Tabriz University of Medical Sciences, Tabriz, Iran. This article is based on a thesis submitted for Pharm D degree (No. 2617) in Faculty of Pharmacy, Tabriz University of Medical Sciences, Tabriz, Iran.

### References

- [1] Abrahamsson B, Alpsten M, Bake B, Jonsson UE, Eriksson-Lepkowska M, Larsson A. Drug absorption from nifedipine hydrophilic matrix extended-release (ER) tablet-comparison with an osmotic pump tablet and effect of food. *J Control Release*. 1998;52(3):301-10.
- [2] Carr AA, Bottini PB, Feig P, Prisant LM, Mulligan S, Devane JG, et al. Effectiveness of once-daily monotherapy with a new nifedipine sustained release calcium antagonist. *The American Journal of Cardiology*. 1992;69(13):28-32.
- [3] Garbacz G, Golke B, Wedemeyer RS, Axell M, Saderlind E, Abrahamsson B, et al. Comparison of dissolution profiles obtained from nifedipine extended release once a day products using different dissolution test apparatuses. *Eur J Pharm Sci*. 2009;38(2):147-55.
- [4] Guyot M, Fawaz F. Nifedipine loaded-polymeric microspheres: preparation and physical characteristics. *Int J Pharm*. 1998;175(1):61-74.
- [5] Higuma T, Oikawa K, Kato T, Mori Y, Kudo T, Yamamoto T, et al. Comparison of the effects of long-acting nifedipine CR and diltiazem R in patients with vasospastic angina: Aomori coronary spastic angina study. *J Cardiol*. 2010;56(3):354-60.
- [6] Huang J, Wigent RJ, Bentzley CM, Schwartz JB. Nifedipine solid dispersion in microparticles of ammonio methacrylate copolymer and ethylcellulose binary blend for controlled drug delivery: Effect of drug loading on release kinetics. *Int J Pharm*. 2006;319(1/2):44-54.
- [7] Hayashi T, Kanbe H, Okada M, Suzuki M, Ikeda Y, Onuki Y, et al. Formulation study and drug release mechanism of a new theophylline sustained-release preparation. *Int J Pharm*. 2005;304(1/2):91-101.
- [8] Kojima H, Yoshihara K, Sawada T, Kondo H, Sako K. Extended release of a large amount of highly water-soluble diltiazem hydrochloride by utilizing counter polymer in polyethylene oxides (PEO)/polyethylene glycol (PEG) matrix tablets. *Eur J Pharm Biopharm*. 2008;70(2):556-62.
- [9] Li FQ, Hu JH, Deng JX, Su H, Xu S, Liu JY. In vitro controlled release of sodium ferulate from Compritol 888 ATO-based matrix tablets. *Int J Pharm*. 2006;324(2):152-7.
- [10] Tanaka N, Imai K, Okimoto K, Ueda S, Tokunaga Y, Ohike A, et al. Development of novel sustained-release system, disintegration-controlled matrix tablet (DCMT) with solid dispersion granules of nilvadipine. *J Control Release*. 2005;108(2/3):386-95.
- [11] Cao QR, Choi HG, Kim DC, Lee BJ. Release behavior and photo-image of nifedipine tablet coated with high viscosity grade hydroxypropylmethylcellulose: effect of coating conditions. *Int J Pharm*. 2004;274(1/2):107-17.
- [12] Hong SI, Oh SY. Dissolution kinetics and physical characterization of three-layered tablet with poly(ethylene oxide) core matrix capped by Carbopol. *Int J Pharm*. 2008;356(1/2):121-9.
- [13] Ishikawa T, Watanabe Y, Takayama K, Endo H, Matsumoto M. Effect of hydroxypropylmethylcellulose (HPMC) on the release profiles and bioavailability of a poorly water-soluble drug from tablets prepared using macrogol and HPMC. *Int J Pharm*. 2000;202(1/2):173-8.
- [14] Pattarino F, Giovannelli L, Bellomi S. Effect of poloxamers on nifedipine microparticles prepared by Hot Air Coating technique. *Eur J Pharm Biopharm*. 2007;65(2):198-203.
- [15] The United States Pharmacopeia 34: The National Formulary 29. Rockville: The United States Pharmacopeial Convention, Inc; 2011.
- [16] Adibkia K, Barzegar-Jalali M, Mohammadi G, Ebrahimnejhad H, Alaei-Beirami M. Effect of sodium alginate chain length and Ca<sup>2+</sup> and Al<sup>3+</sup> on the release of diltiazem from matrices. *Pharmaceutical Sciences*. 2011;16(4):221-8.
- [17] Mohammadi G, Barzegar-Jalali M, Siah Shadbad MR, Azarmi S, Barzegar-Jalali A, Rasekhian M, et al. The effect of inorganic cations Ca<sup>2+</sup> and Al<sup>3+</sup> on the release rate of propranolol hydrochloride from sodium carboxymethylcellulose matrices. *Daru*. 2009;17(2):68-79.



- [18] Varshosaz J, Dehghan Z. Development and characterization of buccoadhesive nifedipine tablets. *Eur J Pharm Biopharm.* 2002;54(2):135-41.
- [19] Barzegar-Jalali M, Adibkia K, Valizadeh H, Siahi-Shadbad MR, Nokhodchi A, Omidi Y, et al. Kinetic analysis of drug release from nanoparticles. *J Pharm Pharm Sci.* 2008;11(1):167-77.
- [20] Mohammadi G, Barzegar-Jalali M, Valizadeh H, Nazemiyeh H, Barzegar-Jalali A, Siahi-Shadbad MR, et al. Reciprocal powered time model for release kinetic analysis of ibuprofen solid dispersions in oleaster powder, microcrystalline cellulose and crospovidone. *J Pharm Pharm Sci.* 2010;13(2):152-61.
- [21] Abrahamsson B, Alpsten M, Bake B, Larsson A, Sjagren J. In vitro and in vivo erosion of two different hydrophilic gel matrix tablets. *Eur J Pharm Biopharm.* 1998;46(1):69-75.
- [22] Portero A, Remuañ-Lopez C, Vila-Jato JL. Effect of chitosan and chitosan glutamate enhancing the dissolution properties of the poorly water soluble drug nifedipine. *Int J Pharm.* 1998;175(1):75-84.
- [23] Tran HTT, Park JB, Hong KH, Choi HG, Han HK, Lee J, et al. Preparation and characterization of pH-independent sustained release tablet containing solid dispersion granules of a poorly water-soluble drug. *Int J Pharm.* 2011;415(1/2):83-8.